



SPREDOX D-564

For Composite Material

Product Description

Spredox D-564 provides outstanding wetting and dispersing effect on fillers material including UPR and composite epoxy material.

Specification	
Active Content	100%
Solvent	-

Test Formulation

Dispersant (100%)	0.36
UPR	24.91
PS/Styrene=6:4	10.68
CaCO3	17.79
Al(OH)3	42.7
Styrene	3.56
Total	100

Dispersion Test

Ingredients are mixed in sequence, then stir the mixture for 5 min. Drop 1 g sample on the test panel and allow free flow for 10 secs. Observe the flow length.

	Vis. cps@2rpm
B brand 9010	34,064.38
D-564	31,519.74

B brand 9010

D-564

